



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: C08F 10/00, 4/606		A1	(11) International Publication Number: WO 97/22635
			(43) International Publication Date: 26 June 1997 (26.06.97)
(21) International Application Number: PCT/US96/20544		(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 18 December 1996 (18.12.96)			
(30) Priority Data: 60/008,893 19 December 1995 (19.12.95) US		Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicant: EXXON CHEMICAL PATENTS INC. (US/US); 5200 Bayway Drive, Baytown, TX 77520-5200 (US)			
(72) Inventors: TURNER, Howard, W.; 21583 LaPlaya Court, Cupertino, CA 95014 (US). SPEED, Charles, S.; 4 Tucker, Dayton, TX 77535 (US). FOLIE, Bernard, J.; 2621 Werlein, Houston, TX 77005 (US). CROWTHER, Donna, J.; 1104 Cactus Drive, Baytown, TX 77521 (US). WALZER, John, F., Jr.; 4101 Nasa Road 1, No. 261, Seabrook, TX 77586 (US). FISHER, Richard, A.; 2216 Fairwater Park Drive, League City, TX 77573 (US). VAUGHAN, George, A.; 3601 Allen Parkway #720, Houston, TX 77019 (US).			
(74) Agents: MULLER, William, G. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).			
(54) Title: HIGH TEMPERATURE OLEFIN POLYMERIZATION PROCESS			
(57) Abstract <p>A polymerization process for olefinically or acetylenically unsaturated monomers is disclosed. The process comprises contacting the one or more of the monomers with a suitable ionic catalyst system in the presence of a long-chain, linear alkyl ligand-containing organoaluminum compound. Preferred ionic catalysts are derived from 1) bridged hafnium compounds, 2) silicon bridged monocyclopentadienyl titanium compounds and 3) unbridged, bulky Group 15 containing bulky monocyclopentadienyl titanium compounds, and a non-coordinating anion precursor compound. A class of preferred anion precursors consists of hydrated salts comprising a Group 1 or 2 cation and a non-coordinating anion. Using the preferred ionic catalysts high temperature processes, e.g., at or above 90 °C can be conducted to prepare polyolefins, particularly ethylene copolymers, of both high molecular weight and high comonomer content.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

HIGH TEMPERATURE OLEFIN POLYMERIZATION PROCESS

5 Field of the Invention

This invention relates to catalyst system selection and high temperature process conditions for polymerization of monomers containing ethylenic or acetylenic unsaturation wherein the catalyst system is single-sited and comprises a transition metal cation and a
10 stabilizing, compatible non-coordinating anion.

Background of the Invention

Ionic catalyst systems for olefin polymerization based on transition metal
15 compounds such as metallocene compounds are recent but now well-known. Such metallocene compounds are based on transition metals capable of supporting at least one *pi*-bound aromatic ligand, typically a cyclopentadienyl or substituted cyclopentadienyl ligand and at least one additional ligand which can be abstracted so as to form a catalytically active cation structure. Co-catalyst anions are needed to stabilize these
20 cations, which are highly reactive, but those anions must be capable of doing so without either closely coordinating with the cation that its reactivity, and thus polymerization activity, is diminished, or transferring an anionic fragment to the cation so as to alter its polymerization capability. Single coordination complexes and multi-nuclear coordination complexes based on the Group IIIA or 13 elements, such as boron or aluminum, have
25 shown particular suitability as effective co-catalyst anion sources. See, the disclosures in EP-A-0 277 003, EP-A-0 277 004 and their equivalents, U.S. patents 5,198,401 and 5,278,119, particularly Examples 27 and 32. Example 32 of '119 discloses the use of bis(trimethylsilyl)cyclopentadienyl hafnium dimethyl as the metallocene compound. Example 27 of '401 lists dimethylsilylbis(indenyl) zirconium dimethyl in column 9, line 16.

alumoxane co-catalyst at a temperature of 70 °C and ethylene pressure of 5 bar. Productivity ranged from 35 to 56 g PE for 1 hour of polymerization reaction. The highest production was reported for $\text{Me}_2\text{Si}(3,4,7\text{-Me}_3\text{Ind})_2\text{ZrCl}_2$.

5 In EP-A1-0 612 768, bridged and unbridged hafnium metallocene compounds stabilized by non-coordinating anions after activated with alkyl-aluminum co-catalysts are said to demonstrate high catalyst activity over the zirconium analogues when utilized in processes at temperatures at or exceeding 120 °C. The medium pressure solution processes are preferably to be conducted at pressures of 500 to 3500 kg/cm². All listed
10 hafnocenes are dichloride-substituted embodiments and each of the working examples of the invention is alkylene bridged, with cyclopentadienyl, indenyl or fluorenyl *pi*-bound ligands.

Catalyst systems based on monocyclopentadienyl titanium compounds
15 activated with alumoxane suitable for the preparation of ethylene- α -olefin copolymers of high molecular weight and high α -olefin content are described in U.S. patent 5,264,405. This patent teaches that the cyclopentadienyl group should be fully substituted with methyl groups and bridged to an amido group having an aliphatic or alicyclic hydrocarbyl ligand bonded through a 1° or 2° carbon. Copolymerization of
20 ethylene with propylene in Example 45 with a bridged monocyclopentadienyl Group 4 metal catalyst compound at 80 °C produced a copolymer with 20 wt.% ethylene having an M_n of about 20,080. In each Example 55 with the same catalyst as with Example 45, at a reaction temperature of 140 °C, an ethylene-propylene copolymer having a density of 0.863, indicative of an amorphous ethylene copolymer, exhibited an
25 M_n of about 46,500.

Due to the sensitivities of ionic catalyst systems to polar impurities, solution polymerization processes utilizing scavenging compounds, for example alkyl aluminum compounds or alkyl alumoxanes, have been described. See, for example, U.S. patents
30 5,153,157 and 5,241,025, describing Group-III A metal scavenger compounds and processes. WO-A-94/07927 addresses a similar process as adapted for

SUBSTITUTE SHEET (RULE 26)

monocyclopentadienyl catalyst systems, it describes advantages of bulky scavengers when the monocyclopentadienyl catalyst compounds do not contain bulky substituents to impede interaction with the scavenging compounds. Triisoprenyl aluminum is exemplified and triisobutyl aluminum is listed along with tri-n-octyl and tri-n-hexyl
5 aluminum as suitable bulky scavengers.

In view of the breadth of the disclosures concerning the use of metallocenes for olefin polymerization, and the general industrial need to employ the most effective catalysts and processes so as to have increased productivities while maintaining both
10 comonomer incorporation and high molecular weight polymer preparation capability, additional investigative efforts were required. In particular general knowledge based on observations in the field gave rise to the traditional understanding that under temperatures exceeding about 80 °C increased comonomer incorporation using metallocene catalysts resulted in lower molecular weight polymer.

15

Invention Disclosure

It has been discovered in resulting investigations that even when subjected to the demanding conditions of high temperature in solution and high pressure processes, high
20 molecular weight ethylene copolymers ($M.I. \leq 10$, preferably, $M.I. \leq 1$) can be polymerized in the presence of stable, single-sited discrete ionic catalyst systems, for example, those having cations derived from the transition metal compound group consisting of 1) bridged, unsubstituted- or substituted-indenyl, or fluorenyl group containing, hafnium compounds; 2) bridged hetero-atom containing, substituted or unsubstituted monocyclopentadienyl
25 titanium compounds; 3) unbridged, bulky Group 15 containing, bulky monocyclopentadienyl titanium compounds; 4) Group 4 or 5 compounds containing bulky chelating diamide ancillary ligands, and 5) Group 8 metal diimine compounds wherein the metal is in a +2 oxidation state, such as Pd(II) and Ni(II). Accordingly the invention is in part a process for copolymerizing ethylene and at least one higher olefin, that is C_3 to C_{20} ,
30 preferably C_4 to C_{10} , alpha-olefin, diolefin, or C_4 to C_{20} cyclic olefin, comprising the step of contacting said monomers with one or more of the stable, single-sited ionic catalysts with a

cation above and a stabilizing, compatible non-coordinating anion in a polymerization reaction with a reaction medium temperature of 90 °C or above, and optionally at a pressure exceeding 50 bar, preferably exceeding 75 bar for solution processes and 500 bar for high pressure supercritical phase processes. The invention is also in part a modified
5 process comprising the additional step of introducing into either the reaction medium, recycle stream or the monomer feedstocks prior to the polymerization reaction, a scavenger for polar impurities, most preferably a trialkyl aluminum each alkyl being a long-chain, linear-alkyl.

10 Detailed Description and Best Mode of the Invention

The bridged hafnium compounds of the invention include those having one or more carbon, silicon, or germanium atoms bridging two cyclopentadienyl (Cp) ligands of the hafnium metal centers, said ligands optionally containing one or more hydrocarbon
15 substituents. When the Cp ligand is an indenyl or fluorenyl group, substitutions can be made either on the 5 or 6 member ring carbon atoms. Substituents typically include one or more C₁ to C₃₀ hydrocarbon groups selected from linear, branched, cyclic, aliphatic, aromatic or combined groups, whether in a fused-ring or pendant configuration. For the purposes of this application the term "hydrocarbon" is meant to include those compounds
20 or groups that have essentially hydrocarbon characteristics but optionally contain not more than about 10 mol.% non-carbon, polar atoms, such as oxygen, sulfur, nitrogen and phosphorous. Similarly the use of hetero-atom containing cyclopentadienyl rings, where a non-carbon atom replaces one of the ring carbons, is considered for this specification to be within the terms "cyclopentadienyl", "indenyl", and "fluorenyl".

25

Specific bridged hafnium catalysts include those derived from: (1) indenyl-based complexes such as the *rac*- or *meso*- isomer of dimethylsilyl bis(indenyl)hafnium dimethyl,
dimethylsilyl bis(4,5,6,7- tetrahydro-indenyl) hafnium dimethyl, dimethylsilyl bis(2-methyl-
indenyl) hafnium dimethyl, dimethylsilyl bis(2-propyl-indenyl) hafnium dimethyl,
30 dimethylsilyl bis(4-methyl, 2-phenyl-indenyl) hafnium dimethyl; (2) cyclopentadienyl complexes such as dimethylsilyl (cyclopentadienyl)(tetramethyl cyclopentadienyl) hafnium

dibenzyl, dimethylsilyl bis(cyclopentadienyl) hafnium dimethyl; and (3) fluorenyl-based complexes such as dibutylsilyl (fluorenyl) (cyclopentadienyl) hafnium dimethyl and dimethylsilyl (indenyl) (fluorenyl) hafnium dihydride, or i-propyl (cyclopentadienyl) (fluorenyl) hafnium dimethyl.

5

In particular, for the bridged bis indenyl hafnium compounds, it has been found that increasing the degree of substitution on the indenyl ligands is effective for increased comonomer incorporation, an effect surprising in view of the general knowledge in the art. Thus when the indenyl substituents include at least two sigma bound hydrocarbon radicals replacing hydrogen atoms on the ring atoms, the performance exceeds that where either of
10 zero substituents or just one substituent are present. For example dimethylsilyl bis(2-methyl, 4-phenyl-indenyl) hafnium dimethyl has been found to provide one or both of higher comonomer incorporation and higher molecular weight as compared to dimethylsilyl bis(2-methyl-indenyl) hafnium dimethyl, which is better in one or both of
15 these features than dimethylsilyl bis(indenyl) hafnium dimethyl. Thus preferably the ligation on the indenyl radicals in the bulky hafnium compounds will generally comprise two or more C₁ to C₃₀ hydrocarbon substituents as defined above.


The silicon bridged hetero-atom containing, substituted or unsubstituted
20 monocyclopentadienyl titanium compounds of the invention are any of those described in the art, see for example those described in U.S. patent 5,264,405, WO 92/00333 and U.S. patent 5,408,017. The substituted cyclopentadienyl ligand is one having hydrocarbon substituents as defined for the cyclopentadienyl, indenyl and fluorenyl ligands of the bridged hafnium compounds above. Each document is incorporated by reference for
25 purposes of U.S. patent practice.

The unbridged, bulky Group 15 containing, bulky monocyclopentadienyl titanium compounds of the invention are unbridged titanium compounds having ancillary ligands including a substituted, bulky cyclopentadienyl ligand, a substituted, bulky Group 15
30 heteroatom ligand, and two uninegative, activation reactive ligands at least one of which that can be abstracted for activation of the remaining metal compound to a catalytically

SUBSTITUTE SHEET (RULE 26)

active state and one of which is either similarly abstractable or has a σ -bond to the transition metal into which an olefin or diolefin can insert for coordination polymerization. Typically, for any of the catalysts of this invention, uninegative, activation reactive ligands are selected from the group comprising hydride, lower alkyl, e.g., C_1 to C_4 , or silyl. The bulky cyclopentadienyl ligand is one having substituents as defined for the cyclopentadienyl, indenyl or fluorenyl ligands of the bridged hafnium compounds above, particularly lower alkyl-substituted ligands, such as tetramethyl and pentamethyl cyclopentadienyl ligands. The bulky Group 15 heteroatom ligand is typically a hydrocarbon substituted Group 15 element, preferably nitrogen, wherein the hydrocarbon substituents are covalently bound to the heteroatom through a secondary or tertiary carbon or silicon atom. See also, copending application U.S. Serial Number 08/545,973, filed October 20, 1995 (Atty. Docket No. 95B059) which is incorporated by reference for purposes of U.S. patent practice.

Ionic catalysts derived from Group IVB metal precursors where the ancillary ligand system does not contain a cyclopentadienyl ligand may also be employed in this invention. In general, these systems will be prepared from an ionic activator or Lewis Acid activator and a Group IVB metal containing precursor of the following general formula:



wherein:

A is an optional bridging substituent,

L₁ and L₂ are the same or different non-Cp ancillary ligands.

25 M is a Group IVB metal, and

R₁ and R₂ are the same or different σ -bonded groups such as hydride or hydrocarbyl.

An example of a suitable non-Cp ancillary ligand system is described in "Conformationally Rigid Diamide Complexes: Synthesis and Structure of Tantalum(III) Alkyne Derivatives", D. H. McConville, *et al*, *Organometallics* 1995, 14, 3154-3156. Among the Group 4 metals, the Group 4 metals are preferred especially those of titanium.

- 5 The Group 4 metal compounds will additionally comprise at least two uninegative, activation reactive ligands at least one of which that can be abstracted for activation of the remaining metal compound to a catalytically active state and one of which is either similarly abstractable or has a σ -bond to the transition metal into which an olefin or diolefin can insert for coordination polymerization. The Group 4 metal compounds having
10 the described ligands can be prepared as illustrated in the *Organometallics* article except that the Group 5 metal halide is replaced with a Group 4 tetrahalide

- The Ni^{2+} and Pd^{2+} complexes of the invention are diimine complexes that can be prepared by methods equivalent to those used for the compounds described in "New
15 $Pd(II)$ - and $Ni(II)$ -Based Catalysts for Polymerization of Ethylene and α -Olefins", M. Brookhart, *et al*, *J. Am. Chem. Soc.*, 1995, 117, 6414-6415. These can be either the dialkyl ether adducts as described, or alkylated reaction products of the described dihalide complexes that can be activated to a cationic state by the anion precursors according to the invention.

20

- In general effective scavenging compounds for ionic polymerization catalysts include those aluminum alkyl compounds listed in U.S. patents 5,153,157 and 5,241,025. The term "scavenger" is used in its art-recognized sense of being sufficiently Lewis acidic to coordinate with polar contaminants and impurities adventitiously occurring in the
25 polymerization feedstreams or reaction medium. In particular, for processes utilizing recycle streams of unconverted monomer for reprocessing, the necessity to use polar compounds as catalyst deactivators, or "killers", such as water or lower alcohols, effectively necessitates the use of scavengers, as does the natural occurrence of polar impurities in monomer feedstreams. It has been discovered, however, that the use of
30 excess scavenger has a deleterious effect on catalyst performance, and that the proper choice of scavenger is important to minimize the effects. Addition of excess scavenger

SUBSTITUTE SHEET (RULE 26)

causes lower productivity, molecular weight and comonomer incorporation. This effect can be easily seen by comparing Examples 1.2, 1.6, 1.7, and 1.8 in Table 1 of the examples section, when the addition of 6 equivalents of triethylaluminum (TEAL) caused an increase in productivity but as more TEAL was added productivity decreased as did the molecular weight and comonomer content of the product. Replacing TEAL with triisobutyl aluminum (TIBA) (Examples 1.9 - 1.12) improved the catalyst performance under excess scavenger conditions but did not completely remedy the situation.

Experiments under high temperature conditions showed similar trends. In order to further improve the performance of the ionic catalyst system, a systematic study of more substituted scavengers was carried out. Based on the observation that TIBA performed better than TEAL, it was expected that more highly substituted aluminum alkyl compounds, such as $\text{Al}(\text{CH}_2\text{CMe}_3)_3$, where Me is methyl, would be superior to TIBA because of the increase steric bulk around the Al atom. Comparative tests under high temperature conditions showed that $\text{Al}(\text{CH}_2\text{CMe}_3)_3$ was inferior to TIBA and caused sudden loss of productivity at very low levels of scavenger. Further studies showed that the preferred scavenger is a long chain, linear tri-alkyl aluminum compound, and that longer chains are preferred over shorter chains.

Non-limiting examples of effective long chain, linear tri-alkyl ligand-containing scavengers include those comprised in the group defined by the formula $\text{M}'\text{R}'\text{R}''\text{R}'''$, where M' is Al, and each of the R groups independently is a C_4 or higher linear, branched or cyclic alkyl group, preferably C_6 or higher, most preferably C_8 or higher. The long chain, linear alkyl aluminums where each alkyl substituent was of a length of C_8 or higher, preferably C_9 and higher were observed to exhibit optimal performance, that defined as having the least deleterious effect when used at a level in excess of the optimum level as described in the following paragraph. Specifically included are: tri-n-octyl-aluminum, tri-n-decyl aluminum, tri-n-dodecyl aluminum, tri-n-hexadecyl aluminum, and the higher carbon number equivalents, e.g., $(\text{C}_{20})_3\text{Al}$, including those with mixed ligation, and mixed scavenger compounds as well. The hydrolyzed derivatives of these alkyl-ligand containing organoaluminum compounds will additionally be suitable. Additionally, it will be apparent

SUBSTITUTE SHEET (RULE 26)

that those scavenging compounds comprising both long-chain, linear and bulky ligands or mixed linear ligands, each ligand as described above, will also be suitable, but perhaps less desirable due to more involved or expensive syntheses.

5 The long chain, linear-alkyl ligand-containing scavengers of the foregoing paragraph will be useful in any insertion polymerization process for olefinically or acetylenically unsaturated monomers with any of the ionic catalyst systems known in the art or those in development, where such make use of non-coordinating anions and the resulting catalyst sensitivities require elimination of polar impurities. Suitable catalyst
10 systems appear in the catalyst references listed in the Background in this application, additional catalysts include those Group 5 and 6 transition metal catalyst systems of WO 94/01471 based on U.S. Serial Number 08/086,772 filed July 1, 1993, the disclosures of which are incorporated by reference for purposes of U.S. patent practice. Examples of suitable process conditions include those of gas phase, solution, slurry or bulk
15 polymerization processes for any polymers or copolymers of two or monomers selected from the group consisting of ethylene, propylene, C_4 - C_{20} α -olefins, strained ring cyclic olefins, macromers of up to 100 or more mer units having olefinic unsaturation in the 1-position, or acetylenically unsaturated monomers. Such processes utilize -50 °C to 300 °C temperature and 0 to 3000 bar pressure. Polymers and copolymers having molecular
20 weights equivalent to an M.I. of 100 and below can be prepared in these processes.

The scavengers, whichever are selected, should be utilized in a manner consistent with the sought productivity, polymer molecular weight, and polymer comonomer content. In particular, only that amount sufficient to neutralize the effects of the adventitious
25 catalyst poisons should be utilized, the better purified the comonomer feedstreams into the reactor and as well the other feedstreams or added reactants and recycle, the less scavenger will be required. The amount is preferably as little as possible and can be adjusted empirically by observing the rates of reaction, adiabatic temperature rise, and other indicators of reaction efficiencies observable in the polymerization process, each
30 being maximized holding all variables other than the addition of scavenger constant.

SUBSTITUTE SHEET (RULE 26)

Excess scavenger has been observed to cause a reduction in productivity, molecular weight and comonomer incorporation.

Means of preparing the ionic catalyst systems comprising cations of the described transition metal compounds and suitable non-coordinating anions are conventionally known, see for example U.S. patent 5,198,401 and WO 92/00333. Typically the methods comprise obtaining from commercial sources or synthesizing the selected transition metal compounds comprising an abstractable ligand, e.g., hydride, alkyl or silyl group, and contacting them with an ionizing non-coordinating anion source or precursor in an aromatic solvent. The anion source acts to ionize the transition metal compounds by abstracting the univalent hydride, alkyl or silyl ligand that complements its total valency. The abstraction leaves the transition metal compounds in a +1 cationic state, which is counterbalanced by the stable, compatible and bulky, non-coordinating anion. See the fuller description in U.S. patent 5,198,401, referred to above. Conditions of adiabatic polymerization processes such as practiced at high pressure, result in temperatures exceeding 160 °C and above. These higher operating temperatures lead to increasing instability that is reflected in more difficult higher olefin comonomer incorporation and reduced molecular weight polymer. However, the single site catalysts of this invention under those same conditions evidence higher stability, greater comonomer incorporation and higher retained molecular weight as evidenced in the tabulated observations below.

The non-coordinating anion sources of the invention includes any of those conventionally known to be useful for olefin polymerization with metallocenes, including those known to be useful with the single cyclopentadienyl containing Group 4 transition metals. A representative listing of suitable anions is in U.S. 5,198,401, EP-A-0 426 637, EP-A-0 427 697, EP-A-0 520 732, EP-A-0 573 403, WO 95/24268 and U.S. patent 5,387,568. Those may be introduced into the catalyst preparation step as either ionic compounds having a cation which abstracts a non-cyclopentadienyl ligand of the transition metal compounds or as neutral compounds which upon abstraction of the non-cyclopentadienyl ligand, leave as a by-product the non-coordinating anion portion. Additionally, it is known that the use of alkylating compounds along with an

anion source enables the use of transition metal compounds having ligands too strongly bound to the transition metal center to be abstracted by the anion source, e.g., transition metal dihalides. Typical alkylating sources may be any of the strongly Lewis acidic organoaluminum compounds such as the lower carbon number alkyl aluminums and alkylalumoxanes. See EP-A-0 500 944, EP-A-0 570 982 and EP-A1-0 612 768 for *in situ* processes describing the reaction of alkyl aluminum compounds with dihalo-substituted metallocene compounds prior to or with the addition of activating anion precursor compounds. Each of the above documents is incorporated by reference for purposes of U.S. patent practice. Most preferably transition metal compounds not having halide ligands on the metal center are used for the ionic catalyst systems of this invention since *in situ* alkylation processes may result in competing reactions and interactions that tend to interfere with the overall polymerization efficiency under conditions of high temperature in accordance with this invention

15 A class of preferred anion precursor compounds are hydrated salts comprising a Group 1 or 2 cation and a non-coordinating anion as described above. The hydrated salts can be prepared by reaction of the metal cation-non-coordinating anion salt with water, for example, by hydrolysis of the commercially available or readily synthesized $\text{LiB}(\text{pfp})_4$, which yields $[\text{Li} \cdot \text{H}_2\text{O}] [\text{B}(\text{pfp})_4]$, where (pfp) is penta- or perfluorophenyl. The by-product of ionization of the abstractable ligand-containing transition metal compounds with this precursor is LiOH which is non-volatile and thus is not recycled in the separation phase wherein the polymer is removed from monomer and any diluent prior to recycle. Tests have shown that this low-cost precursor operates to form ionic catalysts having properties essentially equivalent to those formed with the preferred precursor compounds represented by $[\text{Ph}_3\text{C}][\text{B}(\text{pfp})_4]$ and $[\text{PhMe}_2\text{NH}][\text{B}(\text{pfp})_4]$, Ph representing phenyl and Me representing methyl. As with the long chain, linear-alkyl ligand-containing scavengers noted above, this non-volatile by-product anion precursor will be suitable for use with any of the ionic catalyst systems known in the art or those in development, where such make use of non-coordinating anions. Catalytically suitable transition metal compounds capable of cationization include those Group 4 to 6 and 8 compounds addressed above. Again, examples of such include gas phase, solution, slurry and bulk polymerization processes for

SUBSTITUTE SHEET (RULE 26)

any polymers or copolymers of two or monomers selected from the group consisting of ethylene, propylene, C_4 - C_{20} α -olefins, strained ring cyclic olefins, macromers of up to 100 or more mer units having olefinic unsaturation in the 1-position, or acetylenically unsaturated monomers. Such processes utilize -50 °C to 300 °C temperature and 0 to 5 3000 bar pressure.

Known alkylalumoxanes are additionally suitable as catalyst activators for the invention single-site transition metal compounds comprising halide ligands, however these are less preferred since the alumoxane activators are less temperature stable at or 10 above about 160 °C. The alumoxane component includes all those useful as a catalyst activator, typically such will be an oligomeric aluminum compound represented by the general formula $(R-Al-O)_n$, which is a cyclic compound, or $R(R-Al-O)_nAlR_2$, which is a linear compound. In the general alumoxane formula R is a C_1 to C_5 alkyl radical, for example, methyl, ethyl, propyl, butyl or pentyl and "n" is an integer from 1 to about 50. 15 Most preferably, R is methyl and "n" is at least 4. Alumoxanes can be prepared by various procedures known in the art. For example, an aluminum alkyl may be treated with water dissolved in an inert organic solvent, or it may be contacted with a hydrated salt, such as hydrated copper sulfate suspended in an inert organic solvent, to yield an alumoxane. Generally, however prepared, the reaction of an aluminum alkyl with a 20 limited amount of water yields a mixture of the linear and cyclic species of the alumoxane.

A preferred process of polymerization is that conducted at high pressure, that is at from 200 to 3000 bar, preferably from 500 to 2500 bar in a homogeneous single phase or 25 two fluid phases, with or without unreactive diluents or solvents at temperatures generally above the melting point of the polymer being produced. Such processes are typically known and may include the use of scavenger compounds and catalyst deactivation or killing steps, see for example U.S. patent 5,408,017, WO 95/07941, and WO 92/14766. Each of these documents and their U.S. counterparts are incorporated by reference for 30 purposes of U.S. patent practice. Preferred catalyst deactivators, or killers, include high molecular weight, non-recyclable compounds, such as poly vinyl alcohol which exhibit the

functional capacity to complex with the catalysts so as to deactivate them while not forming volatile polar by-products or residual unreacted compounds.

Another preferred process in which any of the catalyst, cocatalyst and scavenger
5 selections disclosed in this application can be advantageously practiced is that of a
continuous, solution process operated at or above 90 °C to 120 °C, even above 150 °C or
above 160 °C, up to about 300 °C. Typically this process is conducted in an inert
hydrocarbon solvent, linear, cyclic or branched aliphatic, or aromatic, at a pressure of from
20 to 200 bar. The disclosures of U.S. patent applications Ser. No. 08/426,363, filed April
10 21, 1995, and Serial Number. 08/545,973 (Atty. Docket 95B059), filed October 20, 1995,
provide relevant description, even when operated at the elevated temperature ranges under
supercritical conditions disclosed in this application. These documents also are
incorporated by reference for purposes of U.S. patent practice.

15 For optimal polymerization results the processes should be designed or conducted
such that the cocatalyst components, that is the transition metal compounds and the anion
precursor compounds, are maintained separately until just prior to or during
polymerization use in the chosen reactor. An example is the use of dual injection of each
catalyst component directly into the reactor or the use of T- or multi-joint mixing
20 chambers just prior to injection into the reactor. Alternatively the catalyst may be formed
in-situ by the independent addition of ionic activator, ligand stabilized metal halide, and
scavenger directly into the reactor or the use of T- or multi-joint mixing chambers just
prior to injection into the reactor. Additional optimization can be achieved when the
scavenger compound is introduced into the reactor independently of the catalyst system, or
25 compounds.

Though directed specifically for high temperature, particularly high pressure or
solution, processes, it will be apparent that the use of heterogeneous support material such
as polymeric and metal or metalloid oxide supports will enable slurry or gas phase use of
30 the process steps and components described and will likely achieve similar benefits of
higher productivities, higher molecular weights, and higher levels of comonomer

SUBSTITUTE SHEET (RULE 26)

incorporation for the ethylene copolymer products capable of production using the disclosed copolymerizable monomers. Illustrative support methods appear in WO 91/09882, WO 94/00500, WO 94/03506, WO 94/07928, and in WO 96/04319 based on U.S. application Serial Number 08/474,948 filed June 7, 1995, in turn based on U.S. Serial
5 Number 08/285,380 filed August 3, 1994. A suitable slurry process is described in U.S. patent 5,229,478. Each of the foregoing are incorporated by reference for purposes of U.S. patent practice.

The following examples are presented to illustrate the foregoing discussion. All
10 parts, proportions and percentages are by weight unless otherwise indicated. Although the examples may be directed to certain embodiments of the present invention, they are not to be viewed as limiting the invention in any specific respect. Methods of determining MW and monomer contents by GPC and NMR for the illustrative EPC examples of the invention are described in U.S. patent 5,229,478 which is incorporated by reference for
15 purposes of U.S. patent practice. For the following examples certain abbreviations have been utilized for convenience : Cp (cyclopentadienyl), Me(methyl), Ind (indenyl), Ph (phenyl), pfp (pentafluorophenyl), r- (racemic), Et (ethyl), Cp* (permethylated cyclopentadienyl), Cod (cyclododecyl), TOA (tri-n-octyl aluminum), TEAL (triethyl aluminum) and TIBA (triisobutyl aluminum).

EXAMPLES

Part I: Laboratory Screening Experiments

5

The data from batch laboratory tests is summarized in Table I. All polymerizations in Table I were carried out in a one liter stainless steel autoclave in 400 cc hexane with 45 cc hexene under 75 psi (517.11 kPa) ethylene head pressure at 60 °C.

10

In each case the autoclave was filled with the solvent and hexene and heated under 75 psi (517.11 kPa) of ethylene until equilibrium was reached under rapid stirring. The catalyst was introduced into the reactor under these conditions and the temperature was maintained at 60 °C \pm 5 °C for the duration of the run. The product was recovered and analyzed by GPC and ^{13}C NMR spectroscopy to determine the molecular weight and comonomer content. An example of continuous process use of the information contained in Table I follows Example 1.1.

15

Example 1.1

20

A one liter mechanically stirred stainless steel autoclave was filled with 400 ml dry and deoxygenated hexane, 45 ml dry and deoxygenated hexene. The reactor was stirred rapidly, pressurized to 75 psi (517.11 kPa) with ethylene, and heated to 60 °C. A catalyst solution in toluene containing 1.42×10^{-5} moles of $\text{r-Me}_2\text{Si(Ind)}_2\text{HfMe}_2$ and 4.99×10^{-5} $[\text{PhMe}_2\text{NH}][\text{B(pfp)}_4]$ was added to the reactor causing a polymerization reaction to occur. After 30 minutes the reactor was vented and the contents were poured into a flask. The solvent was evaporated to yield 5 grams of and ethylene/hexene copolymer having a $M_n = 151,000$ Daltons, a $M_w = 74,000$ Daltons, and 47.4 wt.% hexene. This represents a productivity of 714 grams PE/gram metallocene.

30

The results of the screening experiments collected in Table 1 demonstrate several important trends. These include the following observations.

- Bridged vs. Unbridged Metallocenes
 - 5 + Bridged have 2-3 times the comonomer incorporation (see Cp_2HfMe_2 vs. $\text{Et}_2\text{SiCp}_2\text{HfMe}_2$ or $\text{CpCp}^*\text{HfMe}_2$ vs. $\text{Me}_2\text{SiCpCp}^*\text{HfMe}_2$).
 - + Bridged complexes produce higher MW products.
 - + Bridged complexes typically show higher activities.
- 10 • $[\text{PhMe}_2\text{NH}][\text{Bpfp}]_4$ vs. $[\text{Ph}_3\text{C}][\text{Bpfp}]_4$ vs. $[\text{Li}\cdot\text{H}_2\text{O}][\text{Bpfp}]_4$
 - + All appear to produce the same polymer at similar rates.
- 15 • The Effect of Scavengers on Catalyst Performance
 - + High levels cause lower MW and comonomer content.
 - + Low levels improve productivity without affecting product.
 - + TIBA better than TEAL in terms of effect on product at high levels of scavenger.
 - + high levels depress productivity.
- 20 • $\text{Me}_2\text{Si}(\text{Ind})_2\text{HfMe}_2$ vs. $\text{Me}_2\text{Si}(4\text{-Me}, 2\text{-PhInd})_2\text{HfMe}_2$
 - + Substituted system shows higher MW even at high comonomer content.
 - + Substituted system shows significant increases in comonomer
 - 25 incorporation.
- The metallocene dichloride route vs. the metallocene dialkyl route

- + The chloride free approach produces high MW and comonomer content products.
- 30 • Zr vs. Hf

SUBSTITUTE SHEET (RULE 26)

+ Hf systems superior in terms of MW and comonomer incorporation.

- Mono-Cp Ti vrs. bis-Cp Hf Catalysts

+ The bis-Cp Hf systems can be modified to have similar performance to the mono-Cp systems.

Part 2: Continuous High Pressure Operation

The polymerization reactions in Table 2 were performed in a stirred 1.5 L steel autoclave reaction vessel which was equipped to perform continuous Ziegler polymerization reactions at pressures up to 2000 bar and temperatures up to 300 °C. The reaction system was supplied with a thermocouple and pressure transducer to measure temperature and pressure continuously, and with means to supply continuously purified compressed ethylene and 1-butene. Pressure was controlled by pressure reduction valve. Equipment for continuously introducing a measured flow of catalyst solution, and equipment for rapidly venting and quenching the reaction, and of collecting the polymer product were also a part of the reaction system. The ability to add scavenger to the fresh feed prior to the reactor was provided by a high pressure pump. The polymerization was performed with a specified molar ratio of ethylene to comonomer and without the addition of a solvent. The temperature of the reactor containing ethylene and comonomer was equilibrated at the desired reaction temperature. The catalyst solution was prepared by mixing a specified amount of solid metallocene component with the activator component in toluene under an inert atmosphere. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate which resulted in the desired reactor temperature. The reactor contents were stirred at 1000 rpm and the reactor feed mass flow rate typically used was 40 kg/hr. Exact run conditions including catalyst preparation metallocene component (M) (g), activator component (A) (g), and total volume of solution (L) scavenger aluminum compound to transition metal compound with molar rate (Al:M), catalyst production polymer production rate (kg polymer/hr) average, comonomer molar feed ratio (e.g. C_4/C_2), reactor mass flow rate (kg/hr), and polymer

SUBSTITUTE SHEET (RULE 26)

characteristics including melt index (g/10 minutes at 190 °C), and weight percent comonomer (determined by IR), are also collected in Table 2. All polymerizations were carried out at 225 °C and 1300 bar. The catalyst solutions were prepared using dry and deoxygenated toluene. An example of how to use the information contained in Table 2 follows Example 2.1.

Example 2.1

Using the reactor design as described above, and using a molar ratio of the ethylene to 1-butene of 0.55 without the addition of a solvent, the temperature of the cleaned reactor containing ethylene and 1-butene was equilibrated at the desired reaction temperature of 225 °C. The catalyst solution was prepared by mixing 0.496 g of solid compound $r\text{-Me}_2\text{Si(Ind)}_2\text{HfMe}_2$ with 0.9788 activator compound $(\text{Ph}_3\text{C})^+\text{B}(\text{pfp})_4^-$ in 20 liter toluene. This catalyst solution was continuously fed by a high pressure pump into the reactor at a rate which resulted in a temperature of 225 °C in the reactor. During this run, ethylene and 1-butene was pressured into the autoclave at a total pressure of 1300 bar. The reactor contents were stirred at 1000 rpm, and the mass feed flow rate through the reactor was held constant at 40 kg/hr. Polymerization was conducted for a 60 to 90 sec. residence time. The yield of polymer product was 6.6 kg/hr. of an ethylene-1-butene copolymer which had a MI of 2.85 and a comonomer incorporation of 13 weight percent butene as measured by IR. Transition metal productivity was calculated at 267 kg polymer/g metallocene.

Table 1

Exp #	Metallocene	Activator	Mole Met	Mole Act.	Scav.	A: M	T (min.)	Yield (gr)	Mw (K)	Mn	MW	Wt % C ₆	Productivity
1.1	r-Me ₂ Si(Ind) ₂ HfMe ₂	[PhMe ₂ NH][B(pfp) ₄]	7.28E-05	2.50E-05	none	none	30	7	149	79	1.8	46.8	1944
1.2	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	1.46E-05	4.88E-06	none	none	30	9	148	78	1.8	49.2	1286
1.3	r-Me ₂ Si(Ind) ₂ HfMe ₂	LiB(pfp) ₄ •H ₂ O	9.10E-05	2.91E-05	none	none	1	26	74	34	2.1	55.5	578
1.4	r-Me ₂ Si(Ind) ₂ HfMe ₂	LiB(pfp) ₄ •H ₂ O	2.83E-05	1.18E-05	TIBA	1	30	19	141	75	1.8	51.4	1357
Comp 1.5	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	3.44E-06	3.25E-06	TEAL	6	30	40	120	53	2.2	50.2	23529
Comp 1.6	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	7.89E-06	7.59E-06	TEAL	76	30	3	51	23.4	2.1	39	769
Comp 1.7	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	8.90E-08	8.68E-08	TEAL	335	30	3.5	34.8	17.5	1.9	31.5	750
Comp 1.8	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	1.21E-06	1.08E-06	TIBA	18	30	17	161	82.7	1.9	44.3	31667
Comp 1.9	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	2.22E-06	2.17E-06	TIBA	50	30	12	138	70.8	1.9	52.4	10909
Comp 1.10	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	6.67E-06	6.51E-06	TIBA	335	30	3.5	92.8	44.8	2.0	47	1061
Comp 1.11	r-Me ₂ Si(Ind) ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	7.89E-06	7.59E-06	TIBA	569	30	8	89.1	47.4	1.8	46.8	2051
* Comp 1.12	r-Me ₂ Si(Ind) ₂ HfCl ₂	[PhMe ₂ NH][B(pfp) ₄]	1.87E-05	6.24E-06	TEAL	16	30	20	77.2	34.8	2.2	36	2000
* Comp 1.13	r-Me ₂ Si(Ind) ₂ HfCl ₂	[Ph ₃ C][B(pfp) ₄]	9.34E-06	3.59E-06	TEAL	32	30	15	96.3	46.7	2.0	40.8	2157
1.14	Cp ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	2.65E-05	8.68E-06	none	none	30	15	351	147	2.3	24.4	170
* Comp 1.15	Cp ₂ HfCl ₂	[PhMe ₂ NH][B(pfp) ₄]	4.08E-05	9.99E-06	TEAL	5	30	13	36.6	22.8	1	11.4	855
1.16	Et ₂ SiCp ₂ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	3.20E-05	3.15E-05	none	none	30	13	86.1	43.7	1.9	43.1	963
1.17	CpCp ⁺ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	9.55E-06	3.25E-06	none	none	30	3	113.9	57.7	1.9	11.1	769
1.18	Me ₂ SiCpCp ⁺ HfMe ₂	[Ph ₃ C][B(pfp) ₄]	1.44E-05	5.42E-06	none	none	30	8	140.5	35.6	3.9	32	1231
1.19	r-Me ₂ Si(4Me,2PhInd) ₂ HfMe ₂	[PhMe ₂ NH][B(pfp) ₄]	1.48E-05	4.99E-06	none	none	30	32	220	108	2.0	56.2	3200
1.20	r-Me ₂ Si(4MeInd) ₂ ZrMe ₂	[Ph ₃ C][B(pfp) ₄]	1.84E-05	1.52E-05	none	none	30	5	87.7	46.3	1.8	38.5	625
1.21	Me ₂ SiCp ⁺ N(Cod)TiMe ₂	[Ph ₃ C][B(pfp) ₄]	3.09E-05	2.49E-05	none	none	30	8	247	98.7	2.5	71.9	593

* In-situ activation, dual functioning of alkylaluminum.
 ..Comp.. indicates comparative example.

Table 2

Exp #	Metallocene (M)	Weight M (gr)	Activator (A)	Weight A (gr)	Volume Toluene (L)	M:A Mole Ratio	Scav	A1:M	C ₄ : C ₃	MI	Production Rate (Kg/hr)	wt% C ₄	KgPE/gm
2.1	r-Me ₂ Si(Ind) ₂ HfMe ₂	0.496	Irityl ⁺ B(pfp) ₃ ⁻	0.978	20	0.94	TOA	33	0.55	2.85	6.6	13	287K
2.2	r-Me ₂ Si(Ind) ₂ HfMe ₂	0.552	DMAH ⁺ B(pfp) ₃ ⁻	0.957	20	0.93	TOA	34	0.55	3.02	6.1	13.7	251K
2.3	r-Me ₂ Si(Ind) ₂ HfMe ₂	0.662	DMAH ⁺ B(pfp) ₃ ⁻	0.932	20	1.1	TOA	32	1	25.1	6.3	25.4	178K
2.4	r-Me ₂ Si(2Me,4PhInd) ₂ HfMe ₂	0.891	DMAH ⁺ B(pfp) ₃ ⁻	1.063	20	0.99	TOA	55	1	63.3	6	38.5	290K
2.5	r-Me ₂ Si(2Me,4PhInd) ₂ HfMe ₂	0.891	DMAH ⁺ B(pfp) ₃ ⁻	1.063	20	1	TOA	9	0.6	9.95	6.8	28.5	55K
2.6	r-Me ₂ Si(2MInd) ₂ HfMe ₂	0.497	DMAH ⁺ B(pfp) ₃ ⁻	0.86	10	1	TOA		0.76	24		24	

Part 3: Continuous High Temperature Solution Process

The polymerization reaction was performed in a stirred, liquid filled 2 L jacketed steel reactor equipped to perform continuous insertion polymerization in presence of an inert C₆ hydrocarbon (naphta) solvent at pressures up to 120 bar and temperatures up to 240 °C. The reactor was typically stirred at 1000 rpm during the polymerization. The reaction system was supplied with a thermocouple and a pressure transducer to monitor changes in temperature and pressure continuously, and with means to supply continuously purified ethylene, 1-octene, and solvent. In this system, ethylene dissolved in the hydrocarbon solvent, 1-octene, tri-n-octyl aluminum (TOA) used as a scavenger, and optionally H₂, are pumped separately, mixed, and fed to the reactor as a single stream, refrigerated to -40 °C using liquid NH₃ as a coolant. The transition metal component (TMC) was dissolved in a solvent/toluene mixture (9/1 vol/vol) whereas the non-coordinating anion (NCA) activator was dissolved in toluene or slurried in the hydrocarbon solvent. Both components were pumped separately, mixed at ambient temperature, and cooled to -1 °C prior to entering the reactor. The reactor temperature was set by adjusting the temperature of an oil bath used as a reservoir for the oil flowing through the reactor wall jacket. Next, the polymer molecular weight (MW) or MI was controlled independently by adjusting the ethylene conversion (% C₂) in the reactor via the catalyst flow rate. Finally, the polymer density was controlled by adjusting the ethylene/1-octene weight ratio in the feed.

The results of ten polymerization experiments performed in the reactor described above with three different TMC's (A = rac-dimethylsilyl bis(1-indenyl) hafnium dimethyl, B = dimethylsilyl bis(2-methyl-4-phenyl-1-indenyl) hafnium dimethyl, and C = dimethylsilyl (tetramethylcyclopentadienyl)butylamino titanium dimethyl) and [PhMe₃NH]B(pfp)₄] used as the activator (NCA) are summarized in Table I. For example, the polymerization reaction in run #1 was carried out at 150 °C and 86.4 bar with A. Solvent, ethylene, and 1-octene were continuously fed to the reactor at a rate of 7 kg/hr., and 0.53 kg/hr., respectively. The 1-octene/ethylene weight ratio in the feed was 0.431 in this case. 3.5 mg/hr. of A dissolved in a 9/1 solvent/toluene (vol/vol) mixture and 4.9 mg/hr. of NCA dissolved in toluene were continuously fed to the reactor, resulting in an ethylene conversion of 80.5% and a 1-octene conversion of 43%. For a reactor residence time of 8 minutes, the polymer yield was 1.22 kg/hr. under these conditions. By adding TOA at a rate of 0.08 mmol/hr. to the feed, the catalyst productivity lined out around 348 kgPE/g A. This experiment resulted in an ethylene/1-octene copolymer containing 18.77 weight % comonomer (FTIR) with a weight-average MW of 88,000 g/mol (GPC), a polydispersity

SUBSTITUTE SHEET (RULE 26)

index of 2.1 (GPC), a MI of 1.4 dg/min., a density of 0.8991 g/cc, and a MIR (I21.6/I2) of 34.

- At constant reactor temperature and feed composition, the polymer MW can be adjusted in this low pressure/high temperature polymerization process by controlling the ethylene conversion in the reactor via the catalyst flow rate; typically, the higher the ethylene conversion, the lower the polymer MW (the higher the MI). The above examples showed that surprisingly both bridged bis (Cp) hafnocenes (A and B) exhibit superior MW and comonomer incorporation capability than the bridged mono(Cp) titanocene (C) does.
- 5 For example, at 140 °C and with a 1-octene/ethylene weight ratio in the feed equal to about 0.43 to 0.44, A and B produced, respectively, a 1.6 MI/0.8937 g/cc copolymer at 87.9% ethylene conversion (run #3) and a 0.62 MI/0.8880 g/cc copolymer at 80.7% ethylene conversion (run #6), whereas (C) produced a 1.5 MI/0.9035 g/cc copolymer at a substantially lower ethylene conversion of 77.1% (run #9). Similarly, at 130 °C and with a
- 10 1-octene/ethylene weight ratio in the feed equal to about 0.93 to 0.94, A produced a 1.23 MI/0.8761 g/cc copolymer at 73.9% ethylene conversion (run #4), whereas (C) made a 3.2 MI/0.8866 g/cc copolymer at a lower ethylene conversion of 69.2% (run #10).

Table 3

run #	TM	MW (TM)	TM	ACT	ACT/TM	AIR3	T	P	C ₆ sol	C ₂	C ₆	C ₆ /C ₂
		g/mol	mg/hr	mg/hr	mol/mol	mmol/hr	°C	bar	kg/hr	kg/hr	kg/hr	kg/hr
1	A	494.5	3.5	4.9	0.86	0.08	150.0	86.4	7.0	1.23	0.530	0.431
2	A	494.5	2.6	3.7	0.88	0.08	159.9	86.3	6.9	1.23	0.530	0.431
3	A	494.5	4.0	5.3	0.82	0.11	142.6	86.5	7.1	1.20	0.530	0.442
4	A	494.5	1.4	2.0	0.88	0.11	130.3	86.9	6.9	1.21	1.140	0.942
5	B	674.5	5.5	6.7	1.03	0.08	149.1	86.4	7.0	1.21	0.510	0.421
6	B	674.5	5.0	6.1	1.03	0.08	139.9	86.5	7.3	1.22	0.520	0.426
7	C	329.9	2.9	7.2	1.02	0.08	159.2	86.5	7.1	1.21	0.520	0.430
8	C	329.9	2.5	6.0	0.99	0.08	150.5	86.5	7.0	1.23	0.520	0.423
9	C	329.9	2.1	5.1	1.00	0.08	140.9	86.7	7.0	1.22	0.530	0.434
10	C	329.9	1.8	4.4	1.01	0.10	131.5	86.6	6.9	1.23	1.140	0.927

C ₂	% conv	C ₆	RI	yield	cat prod	MI	MIR	density	C ₆ inc.	Mw	PDI
		% conv	min	kg/hr	kg PE/g TM	dg/min	121.6/12	g/cc	wt %	g/mol	Mw/Mn
80.5	43.0	8.0	8.0	1.22	348	1.40	34.0	0.8991	18.77	88000.00	2.1
73.1	33.1	8.0	8.0	1.047	413	1.20	32.2	0.9038	16.30	85000.00	2.1
87.9	54.9	7.9	7.9	1.35	336	1.60	53.7	0.8947	21.49	84000.00	2.0
73.9	34.8	7.9	7.9	1.29	922	1.23	31.6	0.8761	30.68		
73.6	53.9	8.1	8.1	1.17	212	1.40	50.0	0.8915	23.65	95000.00	3.6
80.7	66.5	7.8	7.8	1.33	266	0.62	65.8	0.8880	26.05		3.3
69.0	22.5	7.9	7.9	0.95	328	2.10	23.8	0.9121	12.22	91000.00	2.5
73.8	28.3	8.0	8.0	1.05	422	1.90	25.3	0.9082	13.98	91000.00	2.5
77.1	33.1	8.1	8.1	1.12	531	1.50	26.7	0.9035	15.66	97000.00	2.4
69.2	26.3	7.8	7.8	1.15	639	3.20	24.5	0.8866	25.97		

SUBSTITUTE SHEET (RULE 26)

Notes:

- (1) For all runs the catalyst activator was (DMAH)[B(pfp)₄] and the scavenger was tri-n-octyl aluminum.
(2) Other abbreviations above include:

A = r-Me₂Si(Ind)₂HfMe₂

B = Me₂Si(2-Me-4PhInd)₂HfMe₂

C = Me₂SiCp*NbⁿbutylTiMe₂

C₂ = ethylene

C₈ = 1-octene

C₆ = hydrocarbon (naphta)solvent

5

10

SUBSTITUTE SHEET (RULE 26)

CLAIMS:

1. In the method for insertion polymerization of olefinically or acetylenically unsaturated monomers comprising contacting one or more of said monomers under suitable polymerization process conditions with an ionic catalyst system, the improvement which comprises conducting said contacting in the presence of a long-chain, linear-alkyl ligand-containing organo aluminum compound.
2. The method of Claim 1 suitable for the preparation of ethylene copolymers having an $M_I \leq 100$ and a density up to 0.92 g/cc. comprising contacting with or without diluent or solvent, ethylene and one or more comonomers capable of insertion polymerization in the presence of an ionic catalyst system selected from 1) bridged hafnium compounds, 2) silicon bridged monocyclopentadienyl titanium compounds and 3) unbridged, bulky Group 15 containing, bulky monocyclopentadienyl titanium compounds, said contacting conducted at a temperature of not less than 90 °C.
3. The method according to Claim 1 wherein said ionic catalyst system is the reaction product of a catalytically suitable Group 4, 5, or 8 transition metal compound having a univalent hydride, alkyl or silyl ligand and a hydrated salt comprising a Group 1 or 2 cation and a non-coordinating anion.
4. The method according to any of Claims 1 through 3 wherein the ionic catalyst system is prepared by contacting the transition metal compound and anion precursor in the polymerization medium or immediately prior to introduction therein.
5. The method according to any of Claims 1 through 4 wherein said organo aluminum compound is introduced into the reaction vessel independently of the catalyst system and its components.
6. A method for insertion polymerization of olefinically or acetylenically unsaturated monomers comprising contacting one or more of said monomers under suitable polymerization process conditions with an ionic catalyst composition comprising the reaction product of a catalytically suitable Group 4, 5, 6, or 8 transition metal compound having a univalent hydride, alkyl or silyl ligand and a hydrated salt comprising a Group 1 or 2 cation and a non-coordinating anion.

SUBSTITUTE SHEET (RULE 26)

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C08F10/00 C08F4/606		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) IPC 6 C08F		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y	DE 41 39 263 A (BASF) 3 June 1993 see page 7 - page 8; examples 5,6; table 1 ---	1 1,2,4,5
Y	WO 94 07927 A (EXXON) 14 April 1994 cited in the application see page 11, line 29 - line 30; example 3 ---	1,2,4,5
P,X	RESEARCH DISCLOSURES, vol. 388, no. 035, 10 August 1996, XP000635433 "High temperature olefin polymerization process" see the whole document ---	1
A	EP 0 570 982 A (TOSOH) 24 November 1993 see example 4 see claims 1,4,10 see page 5, line 43 - line 45 ---	1,4,5
-/--		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
Date of the actual completion of the international search 4 April 1997		Date of mailing of the international search report 21.04.97
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl, Fax (+ 31-70) 340-3016		Authorized officer Fischer, B

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 4139263 A	03-06-93	NONE	
WO 9407927 A	14-04-94	EP 0668880 A JP 8502094 T	30-08-95 05-03-96
EP 570982 A	24-11-93	JP 5320242 A JP 5320243 A DE 69307015 D US 5434115 A	03-12-93 03-12-93 13-02-97 18-07-95
EP 500944 A	02-09-92	WO 9201723 A KR 9409020 B CA 2066247 A	06-02-92 29-09-94 25-01-92

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.